



“Our strength is in our formulations”

TECHNICAL BULLETIN:

CLC 16-228 A/B

DESCRIPTION: A ROOM TEMPERATURE CURE, TWO COMPONENT EPOXY PATCHING, SEALING COMPOUND. EXCELLENT ADHESION TO PLASTICS AND VARIOUS METALS.

SALES SPECIFICATION:

CLC 16-228A

CLC 16-228B

COLOUR:	RED	AMBER
VISCOSITY (cps) (NOTE 1):	120,000	THIXOTROPIC
SPECIFIC GRAVITY (gm/cm ³):	1.6	0.95
SHELF LIFE:	6 MONTHS	6 MONTHS

HANDLING: (NOTES 1,2 & 5)

MIX RATIO BY WEIGHT (A : B)	100:50
MIXED VISCOSITY (cps):	200,000
POT LIFE (200 gm mass):	15 Minutes.
GEL TIME (200 gm mass):	20 Minutes.

CURE SCHEDULE: (NOTE 3)

24 HRS @ 25⁰C OR 2 HRS @ 60⁰C

CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR:	RED
SPECIFIC GRAVITY (gm/cm ³):	1.3
SHORE HARDNESS:	85D
GUIDE TO OPERATING TEMPERATURE:	(NOTE 7) 125 ⁰ C
LINEAR SHRINKAGE (in/in):	(ASTM D 2566) 0.004
TENSILE STRENGTH (psi.):	(ASTM D 638) 6,000
ELONGATION (%)	(ASTM D 638) 8.0
MOISTURE ABSORPTION (%):	(ASTM D 570) 0.2
TENSILE SHEAR (7 DAYS @ 25 ⁰ C) psi	2,200

Continued.....

NOTES:

- 1) If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.
- 2) The mix ratio must be within $\pm 2\%$ of the stated value and thorough mixing is required to avoid degraded properties.
- 3) Other cure schedules may yield satisfactory results however; these should be determined by the customer for his given application.
- 4) Unless otherwise specified, all measurements are taken at 22⁰C.
- 5) These products may trigger allergic reactions in some individuals. Prevent contact with skin; wash with plenty of soap and water if contact occurs and **Read the Material Safety Data Sheet** before using the materials. **Do Not Breathe Vapours** provide good ventilation and exercise good housekeeping at the work area.
- 6) If stated, the values under “**Electrical Characteristics**” may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.
- 7) If indicated, the “**Guide to Operating Temperature**” is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of a product for a particular operating temperature is application dependent and **may change according to the demands placed upon it in service.**

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESSMENT TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

ISSUE DATE: SEPTEMBER, 1997

ISSUE NO: 1

7-6680 Finch Avenue West, Toronto, Ontario M9W 6C2 Canada

Phone: 800-563-3769, Fax: 416-674-7563

Web site: www.crosslinktech.com , E-mail: info@crosslinktech.com
