



“Our strength is in our formulations”

EPOXY CASTING/POTTING COMPOUND

TECHNICAL BULLETIN:

CLR 1061 / CLH 6070

PRODUCT DESCRIPTION: A TWO COMPONENT, ROOM TEMPERATURE EPOXY SYSTEM, SPECIFICALLY DEVELOPED TO POT ELECTRONIC MODULES. THIS PRODUCT CONTAINS NON-ABRASIVE FILLERS MAKING IT SUITABLE FOR PROCESSING IN AUTOMATIC DISPENSE EQUIPMENT.

SALES SPECIFICATION:

CLR 1061

CLH 6070

COLOUR	GREY	AMBER
VISCOSITY (NOTE 1).....	12,000-20,000 cps	3,000 cps
SPECIFIC GRAVITY	1.65 gm/cm ³	0.97 gm/cm ³
SHELF LIFE	6 MONTHS	6 MONTHS

HANDLING:

1. MIX RATIO BY WEIGHT (A:B)(NOTE 2)..... 100:13.3
(100:23 BY VOL)
2. VISCOSITY (NOTE 4)..... 10,000-14,000 cps
3. POT LIFE OF 200 gm MASS (NOTE 4)..... 20 MINUTES
4. GEL TIME (NOTE 4)..... 30 MINUTES
5. PEAK EXOTHERM OF 200 gm MASS..... 100°C

CURE SCHEDULE (NOTE 3):

24HRS @ R.T. OR 4 HOURS @ 60°C

CURED PROPERTIES:

(NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	GREY
DENSITY	1.5 gm/cm ³
SHORE HARDNESS.....	87D
LINEAR SHRINKAGE	0.5%
TENSILE STRENGTH.....	2,800 psi
ELONGATION.....	4%
GUIDE TO OPERATING TEMPERATURE	105°C

NOTES:

- 1) If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.
- 2) The mix ratio must be within $\pm 2\%$ of the stated value and thorough mixing is required to avoid degraded properties.
- 3) Other cure schedules may yield satisfactory results however; these should be determined by the customer for his given application.
- 4) Unless otherwise specified, all measurements are taken at 22^oC.
- 5) These products may trigger allergic reactions in some individuals. Prevent contact with skin; wash with plenty of soap and water if contact occurs and **Read the Material Safety Data Sheet** before using the materials. **Do Not Breathe Vapours** provide good ventilation and exercise good housekeeping at the work area.
- 6) If indicated, the values under “**Electrical Characteristics**” may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.
- 7) If stated, the “**Guide to Operating Temperature**” is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of a product for a particular operating temperature is application dependent and **may change according to the demands placed upon it in service.**

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE HIS OWN ASSESSMENTS TO DETERMINE ITS SUITABILITY FOR HIS PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTIBLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

DATE PREPARED: FEBRUARY 1986ISSUE NO.: 1

7-6680 Finch Avenue West, Toronto, Ontario M9W 6C2 Canada
Phone: 800-563-3769, Fax: 416-674-7563
Web site: www.crosslinktech.com , E-mail: info@crosslinktech.com
