



CROSSLINK TECHNOLOGY INC.
FORMULATED EPOXIES, URETHANES • CUSTOM CAST ELECTRICAL PARTS



“Our strength is in our formulations”

TECHNICAL BULLETIN:

XRD 1069

DESCRIPTION: A SINGLE COMPONENT, FLAME RETARDANT EPOXY POTTING COMPOUND SPECIFICALLY DEVELOPED FOR ENCAPSULATING PRESSURE SENSITIVE FERRITES. THE SYSTEM HAS GOOD STABILITY AND WILL ADHERE TO A VARIETY OF SUBSTRATES.

SALES SPECIFICATION:

XRD 1069

COLOUR:

BLACK

VISCOSITY (cps) (NOTE 1):

12,000 – 20,000

SPECIFIC GRAVITY (gm/cm³):

1.62 ±0.03

SHELF LIFE:

6 – 8 WEEKS*

* SHELF LIFE CAN BE EXTENDED BY COOL STORAGE.

HANDLING: (NOTES 1,2 & 5)

GEL TIME

30 – 45 minutes @ 125⁰C

CURE SCHEDULE: (NOTE 3)

2 - 4 HOURS @ 100⁰C + 4 HOURS @ 125⁰C + (OPTIONAL 2 HOURS @ 150⁰C)

CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR:

BLACK

SPECIFIC GRAVITY (gm/cm³):

1.62

SHORE HARDNESS:

75/65D

LINEAR SHRINKAGE (in/in):

ASTM D 2566

0.007

TENSILE STRENGTH (psi)

ASTM D 638

1,500

ELONGATION (%):

ASTM D 638

25

THERMAL EXPANSION COEFFICIENT:

(in/in/⁰C X 10⁻⁶)

125

FLAMMABILITY

MEETS U.L.

94 V-0

GUIDE TO OPERATING TEMPERATURE:

(NOTE 7)

155⁰C

ELECTRICAL CHARACTERISTICS: (NOTE 6)

DIELECTRIC STRENGTH (v/mil):	@ 0.125"	450
DIELECTRIC CONSTANT:	@ 1 KHz	4.4
DISSIPATION FACTOR:	@ 1 KHz	0.004
VOLUME RESISTIVITY (ohm-cm):		5X10 ¹⁶

NOTES:

- 1) If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.
- 2) The mix ratio must be within $\pm 2\%$ of the stated value and thorough mixing is required to avoid degraded properties.
- 3) Other cure schedules may yield satisfactory results however; these should be determined by the customer for his given application.
- 4) Unless otherwise specified, all measurements are taken at 22^oC.
- 5) These products may trigger allergic reactions in some individuals. Prevent contact with skin; wash with plenty of soap and water if contact occurs and **Read the Material Safety Data Sheet** before using the materials. **Do Not Breathe Vapours** provide good ventilation and exercise good housekeeping at the work area.
- 6) The values indicated under "**Electrical Characteristics**" may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.
- 7) The "**Guide to Operating Temperature**" is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of a product for a particular operating temperature is application dependent and **may change according to the demands placed upon it in service.**

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESSMENT TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

ISSUE DATE: February, 1996
ISSUE NO.: 1