



CROSSLINK TECHNOLOGY INC.

FORMULATED EPOXIES, URETHANES - CUSTOM CAST PARTS



Our strength is in our formulations

TECHNICAL BULLETIN:

CLS 9600

PRODUCT DESCRIPTION:

A SINGLE COMPONENT, 100% SOLIDS, LOW VISCOSITY, IMPREGNATING COMPOUND FOR COILS AND TRANSFORMERS. THIS PRODUCT IS ALSO SUITABLE FOR SAND CASTING.

SALES SPECIFICATIONS:

CLS 9600

COLOR	AMBER
VISCOSITY (NOTE 1, NOTE 4)	800 - 1,600 cps
SPECIFIC GRAVITY	1.15 ± 0.03 gm/cm ³
SHELF LIFE	3 MONTHS

HANDLING:

MIXED VISCOSITY (NOTE 4)	1,100 cps @ 22 °C
GEL TIME OF 15 gm. mass (NOTE 4)	25.0 Min. @ 125 °C

CURE SCHEDULE (NOTE 3):

RECOMMENDED CURE SCHEDULE:	4 Hrs. @ 125 °C
OPTIONAL POSTCURE	2 Hrs. @ 150 °C

CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	AMBER
DENSITY (gm/cm ³)	1.15
SHORE HARDNESS	85D
GUIDE TO OPERATING TEMPERATURE (°C) (Note 6)	220
LINEAR SHRINKAGE (in/in) (ASTM D 2566)	0.0080
TENSILE STRENGTH (psi) (ASTM D 638)	6,500
TENSILE ELONGATION (%) (ASTM D 638)	7.0
COEFFICIENT OF THERMAL EXPANSION (in/in/°C)	65X10 ⁻⁶
THERMAL CONDUCTIVITY (Cal/Sec.Cm.°C)	8X10 ⁻⁴
FLEXURAL STRENGTH (psi)	9,600

TECHNICAL BULLETIN:**CLS 9600****ELECTRICAL PROPERTIES:**

DIELECTRIC CONSTANT	@1 MHz	3.00
DISSIPATION FACTOR	@1 MHz	0.0100
DIELECTRIC STRENGTH	900 Volts/Mil	10 Mil/Section
ARC RESISTANCE		180 Seconds
VOLUME RESISTIVITY		300 x10 ¹⁴ Ohm/Cm

NOTES

Note1 If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.

Note2 Mix ratio must be within $\pm 2\%$ of the stated amount and thorough mixing is required to avoid degraded final properties.

Note3 Other cure schedules may give satisfactory results, however, these should be determined by the customer for their given circumstances.

Note4 All measurements taken at 22°C unless otherwise specified.

Note5 These products may trigger allergic responses in some individuals. Prevent contact with skin, wash with plenty of soap and water immediately if contact occurs. Do not breathe vapours, provide good ventilation and exercise good housekeeping at work area. Read the Material Safety Data Sheet.

Note6 The "Guide to Operating Temperature" is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of this product for a given operating temperature is application dependent and may change according to the demands placed upon it in operation.

Note7 If indicated, the values under "Electrical Characteristics" may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESSMENTS TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

Issue NO: 4

September 18, 2012