



# CROSSLINK TECHNOLOGY INC.

FORMULATED EPOXIES, URETHANES - CUSTOM CAST PARTS



**TECHNICAL BULLETIN: CLR 1066 / CLH 6930**

## PRODUCT DESCRIPTION:

A TWO COMPONENT, FILLED, ROOM TEMPERATURE CURE EPOXY SYSTEM. THE PRODUCT HAS A LOW EXOTHERM AND LOW SHRINKAGE, MAKING IT SUITABLE FOR CASTINGS LARGER THAN 3 KGS.

SALES SPECIFICATION	CLR 1066	CLH 6930
COLOUR	BLACK	AMBER
VISCOSITY (NOTE 1, NOTE 4)	15000 - 40000 CPS @ 22 °C	100 - 300 CPS @ 22 °C
SPECIFIC GRAVITY	1.67 ± 0.03 gm/cm <sup>3</sup>	0.94 ± 0.02 gm/cm <sup>3</sup>
SHELF LIFE	12 MONTHS	12 MONTHS

## HANDLING:

MIX RATIO BY WEIGHT (A:B) (NOTE 2)	100:12
MIXED VISCOSITY (NOTE 4)	4500 cps @ 22 °C
POT LIFE OF 200 gm. mass (NOTE 4)	30.00 Min. @ 22 °C
GEL TIME OF 200 gm. mass (NOTE 4)	2.00 Hrs. @ 22 °C

## CURE SCHEDULE (NOTE 3):

RECOMMENDED CURE SCHEDULE	48 Hrs. @ 22 °C
ALTERNATE CURE SCHEDULE	4 Hrs. @ 60 °C

## CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	BLACK
DENSITY (gm/cm <sup>3</sup> )	1.55
SHORE HARDNESS	87D
TENSILE STRENGTH (psi) (ASTM D 638)	6300
TENSILE ELONGATION (%) (ASTM D 638)	4.0
TENSILE MODULUS (psi)	190000
HDT(°C) (ASTM D 648)	80
COMPRESSIVE STRENGTH (psi)	13500
COMPRESSIVE MODULUS	220000
FLEXURAL STRENGTH (psi)	10250
FLEXURAL MODULUS (psi)	680000
GUIDE TO OPERATING TEMPERATURE(°C)(NOTE 6)	130
LINEAR SHRINKAGE (in/in) (ASTM D 2566)	0.0040
MOISTURE ABSORPTION (% 24 Hours RT)	0.200
THERMAL CONDUCTIVITY	0.5 W/m•K

## ELECTRICAL PROPERTIES

DISSIPATION FACTOR A	@1	0.0300
DIELECTRIC STRENGTH	550 Volts/Mil	10.0 Mil/Section
ARC RESISTANCE		125 Seconds
VOLUME RESISTIVITY		50 x10 <sup>14</sup> ohm•cm

### NOTES

Note1 If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.

Note2 Mix ratio must be within  $\pm 2\%$  of the stated amount and thorough mixing is required to avoid degraded final properties.

Note3 Other cure schedules may give satisfactory results, however, these should be determined by the customer for their given circumstances.

Note4 All measurements taken at 22°C unless otherwise specified.

Note5 These products may trigger allergic responses in some individuals. Prevent contact with skin, wash with plenty of soap and water immediately if contact occurs. Do not breathe vapours, provide good ventilation and exercise good housekeeping at work area. Read the Material Safety Data Sheet.

Note6 The "Guide to Operating Temperature" is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of this product for a given operating temperature is application dependent and may change according to the demands placed upon it in operation.

Note7 If indicated, the values under "Electrical Characteristics" may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.

### IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESMENTS TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

