



# CROSSLINK TECHNOLOGY INC.

FORMULATED EPOXIES, URETHANES - CUSTOM CAST PARTS



**TECHNICAL BULLETIN:** CLR 1625 / CLH 6333

## PRODUCT DESCRIPTION:

AN UNFILLED, ROOM TEMPERATURE CURE, CLEAR LAMINATING SYSTEM. PRODUCTS LOW VISCOSITY GIVES THE SYSTEM EXCELLENT WET-OUT PROPERTIES TO FIBREGLASS AND OTHER FEINFORCING FIBRES. THE MATERIAL WILL ALSO SATURATE WOOD READILY.

SALES SPECIFICATION	CLR 1625	CLH 6333
COLOUR	AMBER	AMBER
VISCOSITY (NOTE 1, NOTE 4)	2000 - 3000 CPS	200 - 500 CPS
SPECIFIC GRAVITY	1.13 ± 0.03 gm/cm <sup>3</sup>	1.00 ± 0.02 gm/cm <sup>3</sup>
SHELF LIFE	12 MONTHS	12 MONTHS

## HANDLING:

MIX RATIO BY WEIGHT (A:B) (NOTE 2)	100:18 (by vol. 100:20.0)
MIXED VISCOSITY (NOTE 4)	700 cps @ 22 °C
POT LIFE OF 200 gm. mass (NOTE 4)	10.00 Min. @ 22 °C

## CURE SCHEDULE (NOTE 3):

RECOMMENDED CURE SCHEDULE	48 Hrs. @ 22 °C
---------------------------	-----------------

## CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	Amber
DENSITY (gm/cm <sup>3</sup> )	1.10
SHORE HARDNESS	85D
TENSILE STRENGTH (psi) (ASTM D 638)	9000
TENSILE ELONGATION (%) (ASTM D 638)	5.5
TENSILE MODULUS (psi)	220000
FLEXURAL STRENGTH (psi)	14000
FLEXURAL MODULUS (psi)	375000
LINEAR SHRINKAGE (in/in) (ASTM D 2566)	0.0006

## ADDITIONAL INFORMATION

Typical values shown are in laminate form.

## ELECTRICAL PROPERTIES

### VOLUME RESISTIVITY

#### NOTES

Note1 If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.

Note2 Mix ratio must be within  $\pm 2\%$  of the stated amount and thorough mixing is required to avoid degraded final properties.

Note3 Other cure schedules may give satisfactory results, however, these should be determined by the customer for their given circumstances.

Note4 All measurements taken at 22°C unless otherwise specified.

Note5 These products may trigger allergic responses in some individuals. Prevent contact with skin, wash with plenty of soap and water immediately if contact occurs. Do not breathe vapours, provide good ventilation and exercise good housekeeping at work area. Read the Material Safety Data Sheet.

Note6 The "Guide to Operating Temperature" is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of this product for a given operating temperature is application dependent and may change according to the demands placed upon it in operation.

Note7 If indicated, the values under "Electrical Characteristics" may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.

#### IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESMENTS TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

6430 Vipond Drive, Mississauga, Ontario, Canada L5T 1W8 Phone: 1-800-563-3769, (905) 673-0510, Fax: (905) 673-0519 Web site: [www.crosslinktech.com](http://www.crosslinktech.com) , E-mail: [info@crosslinktech.com](mailto:info@crosslinktech.com)

