



CROSSLINK TECHNOLOGY INC.

FORMULATED EPOXIES, URETHANES - CUSTOM CAST PARTS

ISO

9001

REGISTERED
QUALITY SYSTEM

SINCE 1981

Our strength is in our formulations

TECHNICAL BULLETIN:

CLS 9310

PRODUCT DESCRIPTION:

A ONE COMPONENT, LOW VISCOSITY, IMPREGNATING COMPOUND FOR COILS AND TRANSFORMERS.
PRODUCT SHOULD BE STIRRED PRIOR TO USE.

SALES SPECIFICATIONS:

CLS 9310

COLOR	AMBER
VISCOSITY (NOTE 1, NOTE 4)	250 - 600 cps
SPECIFIC GRAVITY	1.10 ± 0.03 gm/cm ³
SHELF LIFE	3 MONTHS

HANDLING:

MIXED VISCOSITY (NOTE 4)	400 cps @ 22 °C
GEL TIME OF 10 gm. mass (NOTE 4)	45.0 Min. @ 125 °C

CURE SCHEDULE (NOTE 3):

RECOMMENDED CURE SCHEDULE:	4 Hrs. @ 125 °C
----------------------------	-----------------

CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	AMBER
DENSITY (gm/cm ³)	1.10
SHORE HARDNESS	85D
GUIDE TO OPERATING TEMPERATURE (°C) (Note 6)	155
LINEAR SHRINKAGE (in/in) (ASTM D 2566)	0.0250
TENSILE STRENGTH (psi) (ASTM D 638)	7,000
TENSILE ELONGATION (%) (ASTM D 638)	8.0
COEFFICIENT OF THERMAL EXPANSION (in/in/°C)	70X10 ⁻⁶
THERMAL CONDUCTIVITY (Cal/Sec.Cm.°C)	7X10 ⁻⁴
MOISTURE ABSORPTION (%)	0.200

TECHNICAL BULLETIN:**CLS 9310**

ELECTRICAL PROPERTIES:		
DIELECTRIC CONSTANT	@1 KHz	3.60
DISSIPATION FACTOR	@1 KHz	0.0040
DIELECTRIC STRENGTH	10 Mil/Section	850 Volts/Mil
ARC RESISTANCE		85 Seconds
VOLUME RESISTIVITY		200 x10 ¹⁴ Ohm/Cm

NOTES

Note1 If a filled resin, setting may occur during transportation or storage. Fillers must be remixed before use.

Note2 Mix ratio must be within $\pm 2\%$ of the stated amount and thorough mixing is required to avoid degraded final properties.

Note3 Other cure schedules may give satisfactory results, however, these should be determined by the customer for their given circumstances.

Note4 All measurements taken at 22°C unless otherwise specified.

Note5 These products may trigger allergic responses in some individuals. Prevent contact with skin, wash with plenty of soap and water immediately if contact occurs. Do not breathe vapours, provide good ventilation and exercise good housekeeping at work area. Read the Material Safety Data Sheet and observe.

Note6 The "Guide to Operating Temperature" is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of this product for a given operating temperature is application dependent and may change according to the demands placed upon it in operation.

Note7 If indicated, the values under "Electrical Characteristics" may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESSMENTS TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

Issue NO: 4

April 28, 2011