



CROSSLINK TECHNOLOGY INC.

FORMULATED EPOXIES, URETHANES - CUSTOM CAST PARTS



TECHNICAL BULLETIN: CLS 9611

PRODUCT DESCRIPTION:

A LOW VISCOSITY, SINGLE COMPONENT, EPOXY POTTING AND ENCAPSULATING COMPOUND. THE PRODUCT HAS EXCELLENT STABILITY AND GOOD ADHESION TO A WIDE RANGE OF SUBSTRATES. THIS PRODUCT MEETS UL94-HB FLAMMABILITY REQUIREMENTS.

SALES SPECIFICATION	CLS 9611
COLOUR	GREY
VISCOSITY (NOTE 1, NOTE 4)	12000 - 20000 CPS @ 20 °C
SPECIFIC GRAVITY	1.62 ± 0.03 gm/cm ³
SHELF LIFE	3 MONTHS

HANDLING:

MIXED VISCOSITY (NOTE 4)	16000 cps @ 22 °C
POT LIFE OF 0 gm. mass (NOTE 4)	90.00 Days. @ 20 °C
GEL TIME OF 0 gm. mass (NOTE 4)	90.00 Min. @ 100 °C

CURE SCHEDULE (NOTE 3):

RECOMMENDED CURE SCHEDULE	2 Hrs. @ 100 °C
POST CURE	4 Hrs. @ 125 °C
OPTIONAL POST CURE	150 @ 150 °C

CURED PROPERTIES: (NOT INTENDED FOR PREPARATION OF SPECIFICATIONS)

COLOUR	GREY
DENSITY (gm/cm ³)	1.62
SHORE HARDNESS	70D
TENSILE STRENGTH (psi) (ASTM D 638)	1500
TENSILE ELONGATION (%) (ASTM D 638)	25.0
FLAMABILITY RATING	UL94-HB (130C.)
GUIDE TO OPERATING TEMPERATURE(°C)(NOTE 6)	155
LINEAR SHRINKAGE (in/in) (ASTM D 2566)	0.0070
MOISTURE ABSORPTION (% 24 Hours RT)	0.200
COEFFICIENT OF THERMAL EXPANSION (in/in/°C)	125 x10 ⁻⁶
THERMAL CYCLE FROM (CELSIUS)	-55
THERMAL CYCLE TO (CELSIUS)	155
THERMAL CYCLES	10

ELECTRICAL PROPERTIES

DISSIPATION FACTOR A	@1	0.0040
DIELECTRIC STRENGTH	450 Volts/Mil	125.0 Mil/Section
VOLUME RESISTIVITY		50 x10 ¹⁴ Ω•cm

NOTES

Note1 If a filled resin, settling may occur during transportation or storage. Fillers must be remixed before use.

Note2 Mix ratio must be within $\pm 2\%$ of the stated amount and thorough mixing is required to avoid degraded final properties.

Note3 Other cure schedules may give satisfactory results, however, these should be determined by the customer for their given circumstances.

Note4 All measurements taken at 22°C unless otherwise specified.

Note5 These products may trigger allergic responses in some individuals. Prevent contact with skin, wash with plenty of soap and water immediately if contact occurs. Do not breathe vapours, provide good ventilation and exercise good housekeeping at work area. Read the Material Safety Data Sheet.

Note6 The “Guide to Operating Temperature” is based on our experience with materials of similar chemistry and/or thermal index. The ultimate suitability of this product for a given operating temperature is application dependent and may change according to the demands placed upon it in operation.

Note7 If indicated, the values under “Electrical Characteristics” may be based on supplier data for products with similar compositions. They are provided only as a guide and the recipient must test each material to determine its suitability for the intended application.

IMPORTANT

THE INFORMATION IN THIS BULLETIN IS BASED ON DATA OBTAINED BY OUR OWN RESEARCH AND IS CONSIDERED ACCURATE. ALL INFORMATION SUPPLIED BY CROSSLINK TECHNOLOGY INC., IS FURNISHED UPON THE EXPRESS CONDITION THAT THE PERSON RECEIVING THE PRODUCT SHALL MAKE THEIR OWN ASSESMENTS TO DETERMINE ITS SUITABILITY FOR THEIR PARTICULAR PURPOSE. NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING SUCH INFORMATION, OR THE RESULTS TO BE OBTAINED FROM THE USE THEREOF; THAT ANY PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE; OR THAT THE USE OF SUCH OTHER INFORMATION OR PRODUCT WILL NOT INFRINGE ANY PATENT.

